

**Gold Extraction Data for 29 Goldstrike Composite Samples  
Kappes, Cassiday & Associates (KCA) Test Results**

KCA Sample No.	Comp ID	Deposit Area	Mine Area	Material Type	Head Assay Au (g/t)	Cyanide Solubility AuCN (%)	Bottle Roll Tests		Column Tests	
							200 mesh (75µm)	10 mesh (1.70mm)	12.5mm (1/2 inch)	25mm (1.0 inch)
83702 A	GS-26	Dip Slope	Dip Slope	oxide	1.247	93.0	90.3	89.9		89.1
83703 A	GS-27	Dip Slope	Dip Slope	oxide	0.328	94.5	88.8	85.5		87.0
83704 A	GS-28	Dip Slope	Dip Slope	oxide	0.305	91.8	90.0	75.9	72.9	
83705 A	GS-29	Dip Slope	Hayassampa	oxide	0.431	81.2	74.7	68.6		66.3
83706 A	GS-30	Dip Slope	Hayassampa	oxide	0.403	94.3	86.0	79.6	82.1	
83707 A	GS-31	Western	Caribou	oxide	0.519	86.7	89.5	84.0		86.0
83708 A	GS-32	Western	Caribou	oxide	0.531	92.3	91.6	88.7		91.9
83709 A	GS-33	Western	Caribou	oxide	0.240	87.5	84.5	81.9		81.6
83710 A	GS-34	Western	Caribou	oxide	1.171	88.8	90.8	90.5	91.7	
83711 A	GS-35	Western	Caribou	oxide	0.810	81.5	93.3	89.9		92.2
83712 A	GS-36	Western	Caribou	oxide	0.468	96.2	90.8	86.3		88.1
83713 A	GS-37	Western	Caribou	oxide	1.854	100.3	94.8	93.3		94.5
83714 A	GS-38	Western	Moosehead	oxide	0.800	101.3	91.6	88.5		90.1
83715 A	GS-39	Western	Moosehead	oxide	0.851	102.2	93.6	92.9		92.2
83716 A	GS-40	Western	Moosehead	oxide	0.457	94.1	90.5	87.3	88.7	
83717 A	GS-41	Western	Moosehead	oxide	0.554	90.3	91.9	85.7	84.6	
83718 A	GS-42	Western	Moosehead	oxide	0.214	84.1	81.0	80.9		87.9
83719 A	GS-43	Western	Moosehead	oxide	1.056	91.9	91.6	85.8	86.0	
83720 A	GS-44	Western	Moosehead	oxide	0.630	100.0	94.2	88.1		90.6
83721 A	GS-45	Western	Moosehead	oxide	2.048	95.2	95.3	88.8		82.2
83722 A	GS-46	Western	Moosehead	oxide	0.295	94.9	84.0	77.3		83.2
83723 A	GS-47	Western	Moosehead	oxide	0.618	85.8	87.4	82.5		81.8
83724 A	GS-48	Western	Moosehead	oxide	1.029	99.1	93.1	89.7		91.2
83725 A	GS-49	Western	Beavertail	oxide	0.258	93.0	81.5	62.4		72.0
83726 A	GS-50	Western	Beavertail	oxide	0.498	90.4	79.6	62.8		65.5
83727 A	GS-51	Western	Beavertail	oxide	0.376	90.4	69.5	64.4		67.2
83728 A	GS-52	Western	Beavertail	oxide	0.730	86.3	78.8	57.8		53.2
83729 A	GS-53	Western	Beavertail	oxide	0.286	87.4	81.4	75.0		78.0
83730 A	GS-54	Western	Beavertail	oxide	0.385	90.9	79.9	63.6		46.4
<b>Weighted Average*</b>							<b>89.7</b>	<b>84.4</b>		<b>84.2</b>