

Viper drill results 2011

Hole ID	From (ft)	To (ft)	Int (ft)	Au g/t	Ag g/t	From (m)	To (m)	Int (m)	Au EqI* (g/t)
PV001	No significant values								
PV002	55	80	25	0.47	4.08	16.8	24.4	7.6	0.559
PV003	0	110	110	1.09	20.98	0.0	33.5	33.5	1.572
and	150	160	10	0.81	11.18	45.7	48.8	3.0	1.065
and	340	355	15	0.65	4.20	103.6	108.2	4.6	0.749
PV004	0	45	45	0.51	5.86	0.0	13.7	13.7	0.640
and	70	90	20	0.60	7.48	21.3	27.4	6.1	0.768
PV005	0	30	30	0.27	6.12	0.0	9.1	9.1	0.410
and	45	60	15	0.28	4.52	13.7	18.3	4.6	0.382

* Au equivalent grade calculated using a \$35/oz Silver and \$1500/oz Gold.

Intervals were calculated using a 0.20 g/t cut-off and maximum 3 m of internal waste.

True thickness of intercepts is unknown at this time due to the presence of both high and low angle controls on mineralization. Pilot Gold employs a rigorous quality control system by inserting a blank, standard or duplicate into the sample stream for every 10 drill samples. All gold values reported are 30 gram Fire Assay with Atomic Absorption finish. All assays were performed by ALS Chemex at their Reno and Vancouver labs following preparation in the Elko lab.